Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-01-18-08** **Date: 22-01-2018**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads 16th, 17th, 18th cross roads at Ravindra Nagara in Ward No. 13 in Shettyhalli Sub Division.
Agency	:	Sri.K.Jagadish, #3424, 6th cross, Gayathri Nagara, Bengaluru - 560021
Customer's Reference	:	EE/DD/WO/191/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-01-2018
Sample ID No	:	2018-01-18-08 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	19-01-2018
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.7	–
2	Finess by Air permeablity method (m^2/kg,Min)	298.4	225m^2/kg, Min
3	Density (gm/cc)	3.13	–
4	Standard Consistency (%)	0.295	Not specified
5	Initial Setting time (minutes)	155 minutes	Not less than 30 minutes
6	Final Setting time (minutes)	285 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method) (mm)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-01-18-08** **Date: 22-01-2018**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads 16th, 17th, 18th cross roads at Ravindra Nagara in Ward No. 13 in Shettyhalli Sub Division.
Agency	:	Sri.K.Jagadish, #3424, 6th cross, Gayathri Nagara, Bengaluru - 560021
Customer's Reference	:	EE/DD/WO/191/17-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	18-01-2018
Sample ID No	:	2018-01-18-08 /02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	18-01-2018

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	355	355	2.4	97.6	90-100
3	20 mm	7102	7457	49.7	50.3	30-70
4	10 mm	4989	12446	83.0	17.0	10-35
5	4.75 mm	2218	14664	97.8	2.2	0-5
6	Pan	336	15000	100.0	0	---

CIVIL PRO BANGALORE Sig..... Date.....

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Date: 22-01-2018

Lab ID	:	**CP-2018-01-18-08**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads 16th, 17th, 18th cross roads at Ravindra Nagara in Ward No. 13 in Shettyhalli Sub Division.
Agency	:	Sri.K.Jagadish, #3424, 6th cross, Gayathri Nagara, Bengaluru - 560021
Customer's Reference	:	EE/DD/WO/191/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-01-2018
Sample ID No	:	2018-01-18-08 /03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	18-01-2018
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	32	32	3.2	96.8	90-100	90-100	90-100	95-100
3	2.36 mm	121	153	15.3	84.7	60-95	75-100	85-100	95-100
4	1.18 mm	199	352	35.2	64.8	30-70	55-90	75-100	90-100
5	600 micron	222	574	57.4	42.6	15-34	35-59	60-79	80-100
6	300 micron	219	793	79.3	20.7	5-20	8-30	12-40	15-50
7	150 micron	152	945	94.5	5.5	0-10	0-10	0-10	0-15
8	Pan	55	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL PRO BANGALORE Sig..... Date.....

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 01/02/2018

Lab ID	:	**CP-2018-01-30-07**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads 16th, 17th, 18th cross roads at Ravindra Nagara in Ward No. 13 in Shettyhalli Sub Division.
Agency	:	Sri.K.Jagadish, #3424, 6th cross, Gayathri Nagara, Bengaluru - 560021
Customer's Reference	:	EE/DD/WO/191/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	30-01-2018
Sample ID No	:	2018-01-30-07 /01
Customer ID	:	CC Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	01/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	CC Pavement	M30	25/01/2018	01/02/2018	149.94 X 150.43 X 149.41	22556	8.426	574.5	25.5	25.4
2	CC Pavement	M30	25/01/2018	01/02/2018	150.02 X 151.97 X 150.55	22798	8.359	594.7	26.1	
3	CC Pavement	M30	25/01/2018	01/02/2018	149.78 X 150.41 X 149.32	22528	8.141	552.2	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 01/02/2018

Lab ID	:	**CP-2018-01-30-07**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads 16th, 17th, 18th cross roads at Ravindra Nagara in Ward No. 13 in Shettyhalli Sub Division.
Agency	:	Sri.K.Jagadish, #3424, 6th cross, Gayathri Nagara, Bengaluru - 560021
Customer's Reference	:	EE/DD/WO/191/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	30-01-2018
Sample ID No	:	2018-01-30-07 /03
Customer ID	:	CC Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	01/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	CC Pavement	M30	25/01/2018	01/02/2018	150.85 X 149.24 X 151.08	22513	8.409	563.8	25.0	25.4
2	CC Pavement	M30	25/01/2018	01/02/2018	151.30 X 150.56 X 150.59	22781	8.163	607.9	26.7	
3	CC Pavement	M30	25/01/2018	01/02/2018	151.82 X 151.45 X 150.85	22993	8.250	562.4	24.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 01/02/2018

Lab ID	:	**CP-2018-01-30-07**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads 16th, 17th, 18th cross roads at Ravindra Nagara in Ward No. 13 in Shettyhalli Sub Division.
Agency	:	Sri.K.Jagadish, #3424, 6th cross, Gayathri Nagara, Bengaluru - 560021
Customer's Reference	:	EE/DD/WO/191/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	30-01-2018
Sample ID No	:	2018-01-30-07 /05
Customer ID	:	CC Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	01/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	CC Pavement	M30	25/01/2018	01/02/2018	149.61 X 151.82 X 149.48	22712	8.319	584.4	25.7	25.4
2	CC Pavement	M30	25/01/2018	01/02/2018	151.19 X 151.53 X 150.78	22909	8.456	605.2	26.4	
3	CC Pavement	M30	25/01/2018	01/02/2018	150.78 X 149.49 X 151.47	22541	8.357	541.2	24.0	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner